

Built Tough for the Road: High Efficiency Roadwork starts with High Quality Hoses



Hot Asphalt Hose

Part Number	Hose ID (inches)	Hose OD (inches)	Rated WP (psi)	Bend Radius (inches)	Weight (lbs)
1310-12	0.75	1.28	300	10	0.67
1310-16	1.00	1.53	300	12	0.89

Application: Applying hot asphalt at nozzle with pressures up to 300 PSI at 350° F constant and up to 400° F intermittent temperatures.

Tube: Black, blend of high temperature polymers especially compounded to resist swelling and embrittlement in hot asphalt service.

Reinforcement: Two braids of high tensile steel wire.

Cover: Yellow, heat, oil, abrasion and weather resistant Neoprene (CR).

Temperature: -40 to 350° F.



Hot Asphalt Applicator Hose

Part Number	Hose ID (inches)	Hose OD (inches)	Rated WP (psi)	Bend Radius (inches)	Weight (lbs)
1856-16	1.00	1.53	250	12	0.89

Application: Applying hot asphalt at nozzle with pressures up to 250 PSI at 350° F constant and up to 400° F intermittent temperatures.

Tube: Black, blend of high temperature polymers especially compounded to resist swelling and embrittlement in hot asphalt service.

Reinforcement: Two braids of high tensile steel wire.

Cover: Black, heat, oil, abrasion and weather resistant Neoprene (CR).

Temperature: -40 to 350° F.



Crack Sealer Hose

Part Number	Hose ID (inches)	Hose OD (inches)	Rated WP (psi)	Bend Radius (inches)	Weight (lbs)
1857-12	0.75	1.28	250	10	0.80
1857-16	1.00	1.53	250	12	1.03

Application: Applying hot asphalt at nozzle with pressures up to 250 PSI at 350° F constant and up to 400° F intermittent temperatures.

Tube: Black, blend of high temperature polymers especially compounded to resist swelling and embrittlement in hot asphalt service.

Reinforcement: Two braids of high tensile steel wire.

Cover: Black, heat, oil, abrasion and weather resistant Neoprene (CR).

Temperature: -40 to 350° F.

